



Designation: A490M – 14a

# Standard Specification for High-Strength Steel Bolts, Classes 10.9 and 10.9.3, for Structural Steel Joints (Metric)<sup>1</sup>

This standard is issued under the fixed designation A490M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification covers two types of quenched and tempered alloy steel, metric heavy hex structural bolts having a tensile strength of 1040 to 1210 MPa.

1.2 These bolts are intended for use in structural connections comparable to those covered under the requirements of the Specification for Structural Joints Using ASTM A325 and A490 bolts, approved by the Research Council on Structural Connections; endorsed by the American Institute of Steel Construction and by the Industrial Fastener Institute.<sup>2</sup>

1.3 The bolts are furnished in nominal bolt diameters M12 to M36, inclusive. They are designated by type denoting chemical composition as follows:

Type	Description
Type 1	Medium carbon alloy steel
Type 2	Withdrawn in 2002
Type 3	Weathering steel

1.4 This specification is applicable to metric heavy hex structural bolts and alternate designs as established by the Research Council in its publication, Specification for Structural Joints Using ASTM and bolts.

1.5 For inch-pound bolts, see Specification A490.

1.6 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.7 The following safety hazards caveat pertains only to the Test Methods portion, Section 13, of this specification: This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.02 on Steel Bolts, Nuts, Rivets and Washers.

Current edition approved Sept. 1, 2014. Published December 2014. Originally approved in 1982. Last previous edition approved in 2014 as A 490M – 14. DOI:10.1520/A0490M-14A.

<sup>2</sup> Available from American Institute of Steel Construction (AISC), One E. Wacker Dr., Suite 700, Chicago, IL 60601-2001, <http://www.aisc.org>.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

- A325 Specification for Structural Bolts, Steel, Heat Treated, 120/105 ksi Minimum Tensile Strength
- A490 Specification for Structural Bolts, Alloy Steel, Heat Treated, 150 ksi Minimum Tensile Strength
- A490M Specification for High-Strength Steel Bolts, Classes 10.9 and 10.9.3, for Structural Steel Joints (Metric)
- A563M Specification for Carbon and Alloy Steel Nuts (Metric)
- A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- D3951 Practice for Commercial Packaging
- E384 Test Method for Knoop and Vickers Hardness of Materials
- E709 Guide for Magnetic Particle Testing
- E1444 Practice for Magnetic Particle Testing
- F436M Specification for Hardened Steel Washers (Metric)
- F568M Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners (Metric) (Withdrawn 2012)<sup>4</sup>
- F606M Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets (Metric)
- F788/F788M Specification for Surface Discontinuities of Bolts, Screws, and Studs, Inch and Metric Series
- F959M Specification for Compressible-Washer-Type Direct Tension Indicators for Use With Structural Fasteners (Metric)
- F1136M Specification for Zinc/Aluminum Corrosion Protective Coatings for Fasteners (Metric) (Withdrawn 2011)<sup>4</sup>
- F1470 Practice for Fastener Sampling for Specified Mechanical Properties and Performance Inspection
- F1789 Terminology for F16 Mechanical Fasteners

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>4</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

\*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Requirements for Type 1 Bolts

Alloy Steel		
Element	Heat Analysis, %	Product Analysis, %
Carbon		
For sizes through M30	0.30–0.48	0.28–0.50
For size M36	0.35–0.53	0.33–0.55
Manganese, min	0.60	0.57
Phosphorus, max	0.040	0.045
Sulfur, max	0.040	0.045
Alloying Elements	A	A
Alloy Steel with Boron Addition		
Element	Heat Analysis, %	Product Analysis, %
Carbon		
For sizes through M30	0.30–0.48	0.28–0.50
For size M36	0.35–0.53	0.35–0.55
Manganese, min	0.60	0.57
Phosphorus, max	0.040	0.045
Sulfur, max	0.040	0.045
Boron	0.0005–0.003	0.0005–0.003
Alloying Elements	A	A

<sup>A</sup>Steel, as defined by the American Iron and Steel Institute, shall be considered to be alloy when the maximum of the range given for the content of alloying elements exceeds one or more of the following limits: Manganese, 1.65 %; silicon, 0.60 %; copper, 0.60 % or in which a definite range or a definite minimum quantity of any of the following elements is specified or required within the limits of the recognized field of constructional alloy steels: aluminum, chromium up to 3.99 %, cobalt, columbium, molybdenum, nickel, titanium, tungsten, vanadium, zirconium, or any other alloying elements added to obtain a desired alloying effect.

TABLE 2 Chemical Requirements for Type 3 Bolts

Element	Heat Analysis, %	Product Analysis, %
Carbon		
Sizes M20 and smaller	0.20–0.53	0.19–0.55
Sizes larger than M20.	0.30–0.53	0.28–0.55
Manganese, min	0.40	0.37
Phosphorus, max	0.035	0.040
Sulfur, max	0.040	0.045
Copper	0.20–0.60	0.17–0.63
Chromium, min	0.45	0.42
Nickel, min	0.20	0.17
or		
Molybdenum, min	0.15	0.14

**F2833** Specification for Corrosion Protective Fastener Coatings with Zinc Rich Base Coat and Aluminum Organic/Inorganic Type

**F2328M** Test Method for Determining Decarburization and Carburization in Hardened and Tempered Threaded Steel Bolts, Screws, Studs, and Nuts (Metric)

**G101** Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

2.2 ASME Standards:<sup>5</sup>

**B1.13M** Metric Screw Threads

**B18.2.3.7M** Metric Heavy Hex Structural Bolts

**B18.24** Part Identifying Number (PIN) Code System Standard for B18 Fastener Products

2.3 ISO Standards:<sup>5</sup>

**7412** Hexagon Bolts for High Strength Structural Bolting With Large Width Across Flats (Short Thread Length)–Product Grade C–Property Classes 8.8 and 10.9

2.4 IFI Standard<sup>6</sup>:

**IFI 144** Test Evaluation Procedures for Coating Qualification Intended for Use on High-Strength Structural Bolts

### 3. Terminology

3.1 Terms used in this specification are defined in Terminology **F1789**, unless otherwise defined herein.

### 4. Ordering Information

4.1 Orders for bolts under this specification shall include the following (see **Note 1**):

4.1.1 Quantity (number of pieces of bolts and accessories);

4.1.2 Size, including nominal bolt diameter, thread pitch, and bolt length;

4.1.3 Name of product: metric heavy hex structural bolts;

4.1.4 Type of bolt (Type 1 or 3). When type is not specified, either Type 1 or Type 3 shall be furnished at the supplier's option;

4.1.5 ASTM designation and year of issue;

4.1.6 Other components such as nuts, washers, and washer-type direct tension indicators, if required;

4.1.7 Certification, if required (see Section 16); and

4.1.8 Protective Coating per Specification **F1136M**, Grade 3, if required. See 5.3.

4.1.9 Protective coating per Specification **F2833**, Grade 1 if required. See 4.3.

4.1.10 Special requirements, if required.

4.1.11 For establishment of a part identifying system, see ASME B18.24.

**NOTE 1**—A typical ordering description follows: 1000 pieces M24 × 3 × 100 mm long, heavy hex structural bolt, Type 1, *ASTM A 490 M– 03*; each with two hardened washers, *ASTM F436M*, Type 1; and one heavy hex nut, *ASTM A563M*, Grade DH.

#### 4.2 Recommended Nuts

4.2.1 Nuts conforming to the requirements of Specification **A563M** are the recommended nuts for use with Specification **A 490M** heavy hex structural bolts. The nuts shall be of the class and have a surface finish for each type of bolt as follows.

Bolt Type and Finish	Nut Class and Finish
1, plain (uncoated)	<b>A563M</b> —10S, 10S3, plain (uncoated)
1, coated in accordance with <b>F1136M</b> , Grade 3 or <b>F2833</b> Grade 1	<b>A563M</b> —10S, 10S3 coated in accordance with <b>F1136M</b> , Grade 5 or <b>F2833</b> Grade 1
3, weathering steel	<b>A563M</b> —10S3, weathering steel

#### 4.3 Recommended Washers

4.3.1 Washers conforming to Specification **F436M** are the recommended washers for use with Specification **A490M**

<sup>5</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

<sup>6</sup> Available from Industrial Fastener Institute (IFI), 6363 Oak Tree Boulevard, Independence, OH 44131, [www.industrial-fasteners.org](http://www.industrial-fasteners.org).



heavy hex structural bolts. The washers shall have a surface finish for each type of bolt as follows.

Bolt Type and Finish	Washer Finish
1, plain (uncoated)	plain (uncoated)
1, coated in accordance with F1136M, Grade 3 or F2833 Grade 1	coated in accordance with F1136M, Grade 3 or F2833 Grade 1
3, weathering steel	weathering steel

#### 4.4 Other Accessories

4.4.1 When compressible washer type tension indicators are specified to be used with these bolts, they shall conform to Specification F959M, Type 10.9.

## 5. Materials and Manufacture

5.1 *Heat Treatment*—Type 1 and Type 3 bolts shall be heat treated by quenching in oil from the austenitic temperature and then tempered by reheating to a temperature of not less than 425°C.

5.2 *Threading*—The threads shall be cut or rolled.

#### 5.3 Protective Coatings:

5.3.1 When a protective coating is required and specified, the bolts shall be coated with Zinc/Aluminum Corrosion Protective Coatings in accordance with F1136M Grade 3, both chromium and non-chromium versions, or Specification F2833 Grade 1, which have been qualified in accordance with IFI 144.<sup>7</sup>

5.3.2 No other metallic coatings are permitted unless authorized by Committee F16. Future consideration of any coating will be based on a review of test results submitted to Committee F16 in accordance with the requirements of IFI 144.

## 6. Chemical Composition

6.1 Type 1 bolts shall be alloy steel conforming to the chemical composition requirements in Table 1. The steel shall contain sufficient alloying elements to qualify it as an alloy steel (see Table 1, Footnote A).

6.2 Type 3 bolts shall be weathering steel conforming to the chemical composition requirements in Table 2. See Guide G101 for methods of estimating the atmospheric corrosion resistance of low alloy steel.

6.3 Product analyses made on finished bolts representing each lot shall conform to the product analysis requirements specified in Table 1 or Table 2, as applicable.

6.4 Applications of heats of steel to which bismuth, selenium, tellurium, or lead has been intentionally added shall not be permitted for bolts. Compliance with this requirement shall be based on a statement on the steel certificate indicating that these elements were not intentionally added.

6.5 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology A751.

<sup>7</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Reports RR:F16-1001, RR:F16-1002, and RR:F16-1003.

## 7. Mechanical Properties

7.1 *Hardness*—The bolts shall conform to the hardness specified in Table 3.

#### 7.2 Tensile Properties:

7.2.1 Except as permitted in 7.2.2 for long bolts and 7.2.3 for short bolts, nominal bolt diameters M24 and smaller having a length of  $2\frac{1}{4}D$  and longer, and nominal bolt diameters larger than M24 having a length of  $3D$  and longer shall be wedge tested full size and shall conform to the minimum and maximum wedge tensile load, and proof load or alternative proof load specified in Table 4. The load achieved during proof load testing shall be equal to or greater than the specified proof load.

7.2.2 When the length of the bolt makes full-size testing impractical, machined specimens shall be tested and shall conform to the requirements specified in Table 5. When bolts are tested by both full-size and machined specimen methods, the full-size test shall take precedence.

7.2.3 Nominal bolt diameters M24 and smaller having a length shorter than  $2\frac{1}{4}D$  down to  $2D$  inclusive, which cannot be wedge tensile tested shall be axially tension tested full size and shall conform to the minimum tensile load and proof load or alternate proof load specified in Table 4. Nominal bolt diameters M24 and smaller having a length shorter than  $2D$  which cannot be axially tensile tested shall be qualified on the basis of hardness.

7.2.4 For bolts on which both hardness and tension tests are performed, acceptance based on tensile requirements shall take precedence in the event of low hardness readings.

## 8. Carburization/Decarburization

8.1 *Definition*—This test is intended to evaluate the presence or absence of carburization and decarburization as determined by the difference in microhardness near the surface and core.

#### 8.2 Requirements:

8.2.1 *Carburization*—The bolts shall show no evidence of a carburized surface when evaluated in accordance with the hardness methods established in Test Method F2328M.

8.2.2 *Decarburization*—Hardness value differences shall not exceed the requirements set forth for decarburization in Test Method F2328M materials.

8.3 *Procedure*—Testing for carburization/decarburization shall be performed in accordance with the microhardness (referee) methods established in Test Method F2328M.

TABLE 3 Hardness Requirements for Bolt Sizes M12 to M36 Inclusive

Nominal Bolt Diameter, mm	Length <sup>a</sup>	Brinell		Rockwell C	
		min	max	min	max
M12 to M24, inclusive	Less than $2D$	311	352	33	38
	$2D$ and longer	...	352	...	38
Over M24 to M36, inclusive	Less than $3D$	311	352	33	38
	$3D$ and longer	...	352	...	38

<sup>a</sup> Heavy hex structural bolts M24 and smaller and shorter than  $2D$  are subject only to minimum and maximum hardness. Heavy hex structural bolts larger than M24 to M36 inclusive and shorter than  $3D$  are subject only to minimum and maximum hardness.



TABLE 4 Tensile Load Requirements for Full-Size Bolts

Nominal Bolt Diameter and Thread Pitch, mm	Stress Area, <sup>A</sup> mm <sup>2</sup>	Tensile Load, <sup>B</sup> kN		Proof Load, <sup>B</sup> kN	Alternative Proof Load, <sup>B</sup> kN
		min	max		
Column 1	Column 2	Column 3	Column 4	Length Measurement Method Column 5	Yield Strength Method Column 6
M12 × 1.75	84.3	87.7	103	70	79.2
M16 × 2	157	163	190	130	148
M20 × 2.5	245	255	296	203	230
M22 × 2.5	303	315	366	251	285
M24 × 3	353	367	427	293	332
M27 × 3	459	477	555	381	431
M30 × 3.5	561	583	679	466	527
M36 × 4	817	850	989	678	768

<sup>A</sup>The stress area is calculated as follows:

$$A_s = 0.7854 [D - (0.9382P)]^2$$

where:

$A_s$  = stress area, mm<sup>2</sup>

$D$  = nominal bolt size, mm, and

$n$  = thread pitch, mm.

<sup>B</sup> Loads tabulated and loads to be used for tests of full-size bolts larger than 36 mm in diameter are based on the following:

Nominal Bolt Diameter, mm	Column 3	Column 4	Column 5	Column 6
M12 to M36 inclusive	1040 MPa	1210 MPa	830 MPa	940 MPa

TABLE 5 Tensile Strength Requirements for Specimens Machined from Bolts

Nominal Bolt Diameter, mm	Tensile Strength, MPa		Yield Strength (0.2 % offset), min, MPa	Elongation in 50 mm, min, %	Reduction of Area, min, %
	min	max			
M12 to M36, inclusive	1040	1210	940	14	40

## 9. Dimensions

### 9.1 Head and Body:

9.1.1 The bolts shall conform to the dimensions for heavy hex structural bolts specified in ASME B18.2.3.7M for nominal bolt diameter M16 to M36 inclusive and ISO 7412 for size M12.

### 9.2 Threads:

9.2.1 Threads shall Metric Coarse Thread Series as specified in ASME B1.13M, and shall have Grade 6g tolerance.

9.2.2 The thread length shall not be changed from that specified for heavy hex structural bolts in ASME B18.2.3.7M and ISO 7412 in 9.1.1. Bolts requiring thread lengths other than those required by this specification shall be ordered under Specification F568M, Class 10.9 and 10.9.3.

## 10. Workmanship

10.1 The allowable limits, inspection, and evaluation of the surface discontinuities, quench cracks, forging cracks, head bursts, shear bursts, seams, folds, thread laps, voids, tool marks, nicks, and gouges shall be in accordance with Specification F788/F788M.

## 11. Magnetic Particle Inspection for Longitudinal Discontinuities and Transverse Cracks

### 11.1 Requirements:

11.1.1 Each sample representative of the lot shall be magnetic particle inspected for longitudinal discontinuities and transverse cracks.

11.1.2 The lot, as represented by the sample, shall be free from nonconforming bolts, as defined in 11.3, when inspected in accordance with 11.2 – 11.2.4.

### 11.2 Inspection Procedure:

11.2.1 The inspection sample shall be selected at random from each lot in accordance with Table 6 and examined for longitudinal discontinuities and transverse cracks.

11.2.2 Magnetic particle inspection shall be conducted in accordance with Guide E709 or Practice E1444. Guide E709 shall be used for referee purposes. If any nonconforming bolt is found during the manufacturer's examination of the lot selected in 11.2.1, the lot shall be 100 % magnetic particle inspected, and all nonconforming bolts shall be removed and scrapped or destroyed.

TABLE 6 Sample Sizes with Acceptance and Rejection Numbers for Inspection of Rejectable Longitudinal Discontinuities and Transverse Cracks

Lot Size	Sample Size <sup>A</sup>	Acceptance Number <sup>A</sup>	Rejection Number
2 to 50	all	0	1
51 to 500	50	0	1
501 to 1200	80	0	1
1201 to 3200	125	0	1
3201 to 10 000	200	0	1

<sup>A</sup> Inspect all bolts in the lot if lot size is less than sample size.



11.2.3 Eddy current or liquid penetrant inspection shall be an acceptable substitute for the 100 % magnetic particle inspection when nonconforming bolts are found and 100 % inspection is required. On completion of the eddy current or liquid penetrant inspection, a random sample selected from each lot in accordance with **Table 6** shall be reexamined by the magnetic particle method. In case of controversy, the magnetic particle test shall take precedence.

11.2.4 Magnetic particle indications of themselves shall not be cause for rejection. If in the opinion of the quality assurance representative the indications may be cause for rejection, a sample taken in accordance with **Table 6** shall be examined by microscopic examination or removal by surface grinding to determine if the indicated discontinuities are within the specified limits.

### 11.3 Definitions:

11.3.1 *Nonconforming Bolts*—Any bolt with a longitudinal discontinuity (located parallel to the axis of the bolt in the threads, body, fillet, or underside of head), with a depth normal to the surface greater than  $0.03D$ , where  $D$  is the nominal diameter in millimetres, shall be considered nonconforming. In addition, any bolt with a transverse crack (located perpendicular to the axis of the bolt in the threads, body, fillet, or underside of head) detectable by magnetic particle inspection when examined as specified in **11.2.4**, shall be considered nonconforming.

## 12. Number of Tests and Retests

### 12.1 Testing Responsibility:

12.1.1 Each lot shall be tested by the manufacturer prior to shipment in accordance with the lot identification control quality assurance plan in **12.2 – 12.5**.

12.1.2 When bolts are furnished by a source other than the manufacturer, the Responsible Party as defined in **18.1** shall be responsible for assuring all tests have been performed and the bolts comply with the requirements of this specification.

12.2 *Purpose of Lot Inspection*—The purpose of a lot inspection program shall be to ensure that each lot as represented by the samples tested conforms to the requirements of this specification. For such a plan to be fully effective, it is essential that secondary processors, distributors, and purchasers maintain the identification and integrity of each lot until the product is installed.

12.3 *Lot Method*—All bolts shall be processed in accordance with a lot identification-control quality assurance plan. The manufacturer, secondary processors, and distributors shall identify and maintain the integrity of each lot of bolts from raw-material selection through all processing operations and treatments to final packing and shipment. Each lot shall be assigned its own lot-identification number, each lot shall be tested, and the inspection test reports for each lot shall be retained.

### 12.4 Lot Definition:

12.4.1 *Standard Lot*—A lot shall be a quantity of uniquely identified heavy hex structural bolts of the same nominal bolt diameter and length produced consecutively at the initial operation from a single mill heat of material and processed at

one time, by the same process, in the same manner, so that statistical sampling is valid. The identity of the lot and lot integrity shall be maintained throughout all subsequent operations and packaging.

### 12.5 Number of Tests:

12.5.1 The minimum number of tests from each lot for the tests specified below shall be as follows:

Tests	Number of Tests in Accordance with
Hardness, tensile strength, proof load	Practice <b>F1470</b>
Coating weight/thickness	Specification <b>F1136M<sup>A</sup></b> or <b>F2833</b>
Surface discontinuities	Specification <b>F788/F788M</b>
Magnetic particle inspection	<b>Table 6</b>
Dimensions and thread fit	ASME B18.2.3.7M and ASME B1.13M

<sup>A</sup>Practice **F1470** applies if the coating specification does not specify a testing frequency.

12.5.2 For carburization and decarburization tests, not less than one sample unit per manufactured lot shall be tested for microhardness.

## 13. Test Methods

### 13.1 Tensile, Proof Load, and Hardness:

13.1.1 Tensile, proof load, and hardness tests shall be conducted in accordance with Test Methods **F606M**.

13.1.2 Tensile strength shall be determined using the Wedge or Axial Tension Testing Method of Full Size Product Method or the Machined Test Specimens Method, depending on size and length as specified in **7.2.1 – 7.2.4**. Fractures on full-size tests shall occur only in the bolt threads and no fracture shall occur at the junction of the head and body.

13.1.3 Proof load shall be determined using Method 1, Length Measurement, or Method 2, Yield Strength, at the option of the manufacturer.

13.2 *Carburization/Decarburization*—Tests shall be conducted in accordance with Test Method **F2328M** Hardness Method.

13.3 *Microhardness*—Tests shall be conducted in accordance with Test Method **E384**.

13.4 *Magnetic Particle*—Inspection shall be conducted in accordance with Section **11**.

## 14. Inspection

14.1 If the inspection described in **14.2** is required by the purchaser, it shall be specified in the inquiry and contract or order.

14.2 The purchaser's representative shall have free entry to all parts of manufacturer's works or supplier's place of business that concern the manufacture of the material ordered. The manufacturer or supplier shall afford the purchaser's representative all reasonable facilities to satisfy him that the material is being furnished in accordance with this specification. All tests and inspections required by the specification that



are requested by the purchaser's representative shall be made before shipment, and shall be conducted as not to interfere unnecessarily with the operation of the manufacturer's works or supplier's place of business.

## 15. Rejection and Rehearing

15.1 Disposition of nonconforming bolts shall be in accordance with the section titled "Disposition of Nonconforming Lots" in Practice **F1470**.

## 16. Certification

16.1 When specified on the purchase order, the manufacturer or supplier, whichever is the responsible party as defined in Section **17**, shall furnish the purchaser a test report that includes the following:

16.1.1 Heat analysis, heat number, and a statement certifying that heats having bismuth, selenium, tellurium, or lead intentionally added were not used to produce the bolts;

16.1.2 Results of hardness, tensile, and proof load tests;

16.1.3 Results of magnetic particle inspection for longitudinal discontinuities and transverse cracks;

16.1.4 Results of tests and inspections for surface discontinuities including visual inspection for head bursts;

16.1.5 Results of carburization and decarburization tests;

16.1.6 Statement of compliance with dimensional and thread fit requirements;

16.1.7 Lot number and purchase order number;

16.1.8 Complete mailing address of responsible party; and

16.1.9 Title and signature of the individual assigned certification responsibility by the company officers.

16.2 Failure to include all the required information on the test report shall be cause for rejection.

## 17. Responsibility

17.1 The party responsible for the fastener shall be the organization that supplies the fastener to the purchaser.

## 18. Product Marking

18.1 *Manufacturer's Identification*—All Type 1 and Type 3 bolts shall be marked by the manufacturer with a unique

identifier to identify the manufacturer or private label distributor, as appropriate.

18.2 *Grade Identification*:

18.2.1 Type 1 bolts shall be marked "A 490M."

18.2.2 Type 3 bolts shall be marked "A 490M" underlined.

The use of additional distinguishing marks to indicate the bolts are weathering steel shall be at the manufacturer's option.

18.3 *Marking Location and Methods*—All marking shall be located on the top of the bolt head and shall be either raised or depressed at the manufacturer's option.

18.4 *Acceptance Criteria*—Bolts that are not marked in accordance with these provisions shall be considered nonconforming and subject to rejection.

18.5 Type and manufacturer's or private label distributor's identification shall be separate and distinct. The two identifications shall preferably be in different locations and, when on the same level, shall be separated by at least two spaces.

## 19. Packaging and Package Marking

19.1 *Packaging*:

19.1.1 Unless otherwise specified, packaging shall be in accordance with Practice **D3951**.

19.1.2 When special packaging requirements are required, they shall be defined at the time of the inquiry and order.

19.2 *Package Marking*:

19.2.1 Each shipping unit shall include or be plainly marked with the following information:

19.2.1.1 ASTM designation and type,

19.2.1.2 Size, including nominal bolt diameter, thread pitch, and bolt length,

19.2.1.3 Name and brand or trademark of the manufacturer,

19.2.1.4 Number of pieces,

19.2.1.5 Lot number,

19.2.1.6 Purchase order number, and

19.2.1.7 Country of origin.

## 20. Keywords

20.1 alloy steel; bolts; metric; SI; steel; structural; weathering steel

## SUMMARY OF CHANGES

Committee F16 has identified the location of selected changes to this standard since the last issue (F490M-12) that may impact the use of this standard. (Approved September, 2014.)

(1) *Revised*— **13.1.2** to limit acceptable fractures to threads only.

Committee F16 has identified the location of selected changes to this standard since the last issue (F490M-12) that may impact the use of this standard. (Approved August 1, 2014.)

(1) *Revised*— **5.3.1** and footnote 7.



*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*